PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)


(51) International Patent Classification ⁶ : G02F 1/1337	A1	(11) International Publication Number: WO 99/18474
		(43) International Publication Date: 15 April 1999 (15.04.99)
(21) International Application Number: PCT/GB9	8/030	(GB). WOOD, Emma, Louise [GB/GB]; DERA Malvem, St. Andrews Road, Malvem, Worcs. WR14 3PS (GB).
(22) International Filing Date: 8 October 1998 (0) (30) Priority Data:	8.10.9	 (74) Agent: LAWRENCE, Richard, Anthony; Hewlett-Packard Limited, Intellectual Property Section, Filton Road, Stoke Gifford, Bristol BS34 8QZ (GB).
9721214.6 8 October 1997 (08.10.97) 9721215.3 8 October 1997 (08.10.97) 9721229.4 8 October 1997 (08.10.97) 9721256.7 8 October 1997 (08.10.97)	G	BB (81) Designated States: CN, JP, KR, SG, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).
(71) Applicants (for all designated States except HEWLETT-PACKARD COMPANY [US/US]; Hanover Street, Palo Alto, CA 94304 (US). THE STARY OF STATE FOR DEFENCE [GB/GB]; Evaluation and Research Agency, Ively Road, Famble Hampshire GU14 0LX (GB).	; 30 SECR Defen	OO Published E- With international search report.
(72) Inventors; and (75) Inventors/Applicants (for US only): BRYAN-BROW Peter [GB/GB]; DERA Malvem, St. Andrews Malvem, Worcs. WR14 3PS (GB). HUI, Victor, C [GB/GB]; DERA Malvem, St. Andrews Road, Worcs. WR14 3PS (GB). JONES, John, Clifford [O DERA Malvem, St. Andrews Road, Malvem, WR14 3PS (GB). SAGE, Ian, Charles [GB/GB];	rs Roa Chakla Malver GB/GE Word	id, am

(54) Title: LIQUID CRYSTAL DEVICE ALIGNMENT

Malvern, St. Andrews Road, Malvern, Worcs. WR14 3PS

(57) Abstract

Liquid crystal devices are formed by a layer of a liquid crystal material enclosed between two cell walls, both carrying electrode structures, and one or both walls treated to align molecules of the liquid crystal material. Most alignment treatment give alignment and surface pretilt with a strong azimuthal and zenithal anchoring energy to contacting liquid crystal molecules. The invention reduces at least one of the azimuthal zenithal or translational anchoring energy to improve switching characteristics and optical performance by allowing movement of liquid crystal molecules at or close to the cell wall. The reduction of anchoring energy may be achieved by an oligomer or short chain polymer which is either spread on the surface or added to the liquid crystal material. The size of oligomer or short chain polymer is low enough that it does not appreciably phase separate from the liquid crystal material. The polymer layer has the characteristics of having imperfect solubility in the liquid crystal material used in the device, of having a physical affinity for the surface of the



substrate, and of retaining a substantially liquid like surface at the polymer/liquid crystal interface. The polymer may be formed by polymerisation of reactive low molecular weight materials in solution in the liquid crystal fluid. The resulting solution or dispersion of polymer in liquid crystal is then filled into the cell, and the polymer is allowed to coat the substrate surfaces.